


**PROCESS DETAILS**

Process	EPITAXIAL PLANAR
Die Size	19 x 19 MILS
Die Thickness	9.0 MILS
Base Bonding Pad Area	3.5 x 4.3 MILS
Emitter Bonding Pad Area	3.5 x 4.5 MILS
Top Side Metalization	Al - 30,000Å
Back Side Metalization	Au - 18,000Å

**GEOMETRY**



**GROSS DIE PER 4 INCH WAFER**







30,600

**PRINCIPAL DEVICE TYPES**

2N2905A  
2N2907A  
CMPT2907A  
CMST2907A  
CXT2907A  
CZT2907A  
PN2907A

145 Adams Avenue  
Hauppauge, NY 11788 USA  
Tel: (631) 435-1110  
Fax: (631) 435-1824  
www.centrasemi.com

R3 (1-August 2002)



145 Adams Avenue  
Hauppauge, NY 11788 USA  
Tel: (631) 435-1110  
Fax: (631) 435-1824  
www.centalsemi.com

R3 (1-August 2002)