PLF 263441 C

PLF263441.04/05

Lithiumcobaltoxide-Graphite /

340 (at C/5 from 4.2 V to 3.0 V at 20 °C)

320 (at C/5 from 4.2 V to 3.0 V at 20 °C)

Constant Current + Constant Voltage

3

Polymer Lithium Electrolyte

66520

Pending

3.7 (average)

41 + 0.2 - 0.3

4.20 (+/- 50 mV)

Standard Charge: C/2 Rapid Charge:

Standard Charge: 5 Rapid Charge:

2.6 (max 2.8 Bending)

34 - 0.5

36.5 + 0.5

8

C/50

3.0



Preliminary Data Sheet ¹

Type Designation Type Number Cell Code System

UL Recognition

Nominal Voltage [V] Typical Capacity [mAh] Minimum Capacity C [mAh]

Dimensions [mm] Length (I) Width (w) Height (h) Pouch (a)

Weight, approx. [g]

Charging Method Charge Voltage [V] Initial Charge Current [mA]

Charging Cut-Off (a) or (b) a) by time [h]

b) by min. current [mA]

Discharge Cut-Off voltage [V]

Max. Pulse Discharge Current [mA] 3C @ 2s

Max. Continuous Discharge Current [mA] 2C

Operating Temperature [°C] 0 to 45 Charge: Discharge: -20 to 60

Storage Temperature 1 Year at -20 to 20 °C >80 Capacity Recovery Rate 2) [%] 3 Month at -20 to 45 ℃ 1 Month at -20 to 60 °C >80

Impedance Initial $[m\Omega]$ < 100 @ 1kHz

> 500 (>70 % of Cmin) Life Expectancy 1C/1C, 20°C [Cycles]

After storage at initial cell voltage of 3.7 to 3.9 V/cell; capacity C/5 measured at 20 ℃.

Prior to use read Handling Precaution and Prohibitions for VARTA PoLiFlex® Batteries

Subject to change without prior notice!

VARTA Microbattery GmbH

Daimlerstr. 1, D-73479 Ellwangen, Germany

Tel: (+49)7961-921-0; Fax: (+49)7961-921-553

Version: 06/WoS