FERROXCUBE

DATA SHEET

U46/40/28
U, I cores and accessories

New data 2008 Sep 01




U, I cores and accessories

U46/40/28

U CORES

Effective core parameters

SYMBOL	PARAMETER VALUE U		UNIT
Σ(I/A)	core factor (C1)	0.464	mm ⁻¹
V _e	effective volume	71300	mm ³
l _e	effective length	182	mm
A _e	effective area	392	mm ²
A _{min}	minimum area	392	mm ²
m	mass of core half	≈ 182	g



Core halves

 $\ensuremath{A_L}$ measured on a combination of 2 U cores.

GRADE	A _L (nH)	μ _e	TYPE NUMBER
3C90	6000 ± 25 %	≈ 221 5	U46/40/28-3C90
3F3	5100 ± 25 %	≈ 1880	U46/40/28-3F3

Cores can be gapped on request in one leg.

Properties of core sets under power conditions

	B (mT) at		CORE LOSS (W) at	
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; B = 200 mT; T = 100 °C	f = 400 kHz; B = 50 mT; T = 100 °C
3C90	≥ 320	≤ 9.6	≤ 45	_
3F3	≥ 320	≤ 9.6	_	≤ 45

2008 Sep 01 1337

U, I cores and accessories

U46/40/28

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

2008 Sep 01 1338