

Technical Information SheetKlinger Graphite Laminate SLS

FARNELL CODES:- 7114620, 7114631, 7114643 & 7114655

Compressibility ASTM F36A 40-50%

Recovery 10-15%

Density of graphite $1.0 \pm 5\%$

Leachable chloride content max 50ppm

Purity of graphite min 98%

Insert AISI 316, 0.05mm

Stress relaxation DIN 52913, 50MPa, 300°C min 46 MPa

Continuous service temp max 460°C

Standard thickness 0.45, 0.8, 1.0, 1.5,

2.0, 3.0mm

Thickness tolerance \pm 5% of nominal thickness

Standard sheet size $1000 \times 1000 \pm 5 \text{mm}$

Rolls For thicknesses 0.45 to 1.0mm

only size: 1m wide, 30 to 100m

long

All information and recommendations contained in this specification sheet are to the best of our knowledge correct. Since conditions of use are beyond our control, users must satisfy themselves that products are suitable for the intended processes and uses. No warranty is given or implied in respect of information or recommendations or that any use of products will no infringe rights belonging to other parties. In any event or occurrence our liability is limited to our invoice value of the goods delivered by us to you. We reserve the right to change product design and properties without notice.

Klinger Limited The Klinger Building Wharfedale Road Euroway Trading Estate Bradford BD4 6SG Tel (01274) 688222 Fax (01274) 688549 Telex 517036

International Tel +44 1274 688222 Fax +44 1274 688549

