

# SuperBlue™ LEDs C430CB290-S0100

Cree's SuperBlue LEDs combine highly efficient GaN with Cree's proprietary G•SiC® substrate to deliver the ultimate price/performance for high-intensity blue LEDs. The C430CB290-S0100 is designed for use in high ambient-light conditions with a typical output of 1150  $\mu$ W and a 465 nm dominant wavelength (at 20 mA). Cree's CB series chips are sorted onto tape and compatible with most radial and SMT LED assembly processes.


#### FEATURES

- High Performance 1150  $\mu$ W
- Superior SiC Substrate Technology
- 465 nm Dominant Wavelength
- Excellent Chip-to-Chip Consistency
- High Reliability

### APPLICATIONS

- Full-Color Displays & Moving Message Signs
- Solid-State Incandescent Replacement Bulbs
- High Ambient Panel Indicators
- Color Printers & Scanners
- Medical & Analytical Instruments

## C430CB290-S0100 Chip Diagram



Datasheet: CPR3L, Rev. M



Maximum Ratings at T <sub>A</sub> = 25°C <sup>Notes 1&amp;3</sup>	C430CB290-S0100
DC Forward Current	30 mA
Peak Forward Current (1/10 duty cycle @ 1kHz)	70 mA
LED Junction Temperature	125°C
Reverse Voltage	5 V
Operating Temperature Range	-40°C to +100°C
Storage Temperature Range	-40°C to +100°C
Electrostatic Discharge Threshold (HBM) Note 2	1000 V
Electrostatic Discharge Classification (MIL-STD-883E) Note 2	Class 2

Typical Electrical/Optical Characteristics at T <sub>A</sub> = 25°C, If = 20 mA Note 3											
Part Number	Volt	vard tage , V)		nt Flux µW)	Reverse Current [I(Vr=5V), μΑ]	Flux (mlm)	Peak Wavelength (λ <sub>a</sub> , nm)	Dominant Wavelength ( $\lambda_{a'}$ nm)		th	Full Width Half Max (λ <sub>p</sub> , nm)
	Тур.	Max.	Min.	Тур.	Max.	Тур.	Тур.	Min.	Тур.	Max.	Тур.
C430CB290-S0100	4.0	4.5	850	1150	10	65	428	462	465	466	60

Mechanical Specifications	C430CB290-S0100		
Description	Dimension	Tolerance	
P-N Junction Area (µm)	246 x 246	± 25	
Top Area (µm)	275 x 275	± 25	
Bottom Area (µm)	275 x 275	± 25	
Chip Thickness (µm)	250	± 25	
Au Bond Pad Diameter (µm)	115	± 20	
Au Bond Pad Thickness (µm)	1.2	± 0.5	
Back Contact Metal Area (µm)	20	-5, +10t	

#### Notes:

- Maximum ratings are package dependent. The above ratings were determined using a T-1 3/4 package (with Hysol OS4000 epoxy) for characterization. Ratings for other packages may differ. The forward currents (DC and Peak) are not limited by the die but by the effect of the LED junction temperature on the package. The junction temperature limit of 125°C is a limit of the T-1 3/4 package; junction temperature should be characterized in a specific package to determine limitations. Assembly processing temperature must not exceed 325°C (<5 seconds).</li>
- Product resistance to electrostatic discharge (ESD) according to the HBM is measured by simulating ESD using a rapid avalanche energy test (RAET). The RAET procedures are designed to approximate the maximum ESD ratings shown. The RAET procedure is performed on each die. The ESD classification of Class 2 is based on sample testing according to MIL-STD-883E.
- 3. All products conform to the listed minimum and maximum specifications for electrical and optical characteristics when assembled and operated at 20 mA within the maximum ratings shown above. Efficiency decreases at higher currents. Typical values given are within the range of average values expected by the manufacturer in large quantities and are provided for information only. All measurements were made using lamps in T-1 3/4 packages (with Hysol OS4000 epoxy). Optical characteristics measured in an integrating sphere using Illuminance A.
- 4. Specifications are subject to change without notice.

Cree, Inc. 4600 Silicon Drive Durham, NC 27703 USA Tel: +1.919.313.5300 Fax: +1.919.313.5778 www.cree.com

Copyright © 1998-2006 Cree, Inc. All rights reserved. The information in this document is subject to change without notice. Cree, the Cree logo and G•SiC are registered trademarks, and SuperBlue is a trademark of Cree, Inc.