MODEL TLL-5902

International size reference: 1/2AA, ER14252


TECHNICAL DATA

Li metal content


(Typical values @+25 °C for batteries stored for one year or less)

Nominal capacity @ 1 mA, to 2V	1.1 Ah
Rated voltage	3.6 V
Maximum recommended continuous current	50 mA
Maximum pulse current capability	100 mA
Weight	9.6 g (0.339 oz)
Volume	4 cc
Operating temperature range	-55 °C to +85 °C

** U.L. Component Recognition, MH 12193









approx. 0.35 g

TERMINATIONS & ORDERING NO.

SUFFIX- /S STANDARD	15-5902-21530
SUFFIX- /T SOLDER TABS	15-5902-31530
SUFFIX- /P AXIAL PINS	15-5902-41530
SUFFIX- /PT2 RADIAL PINS	15-5902-36530
SUFFIX- /TP POLARIZED TABS	15-5902-52530
SUFFIX- /PT POLARIZED TABS	15-5902-53530





iXtra - Long Term High Performance


Note: Any presentations in this data sheet concerning performance are for information purpose only and are not construed as warranties either expressed or implied, of future performance.

Rev. C 11/05

<u>TLL-5902</u>

CELL FEATURES

- 3.6 V Primary lithium-thionyl chloride (Li-SOCI2)
- Fast voltage recovery after long term storage and/or usage
- High energy density
- High and stable operating voltage
- Low self discharge rate
- 10 years shelf life
- Bobbin construction
- Hermetic glass-to-metal-sealing
- Non-flammable electrolyte
- Non-restricted for transportation






MAIN APPLICATIONS


- Utility meters (elect., water & gas)
- Automatic meter reading
- RF systems
- Sensors & monitoring systems
- Tracking systems
- Wireless security systems
- Automotive electronics
- Industrial electronics
- Ultra Low Power (ULP) devices
- Others

STORAGE CONDITIONS

- Cells should be stored in a clean& dry (less than 30 % RH) area
- Temp. should not exceed +30 °C

For updated information please visit our website **www.tadiranbat.com**





iXtra - Long Term High Performance

Note: Any presentations in this data sheet concerning performance are for information purpose only and are not construed as warranties either expressed or implied, of future performance.

Rev. C 11/05