FERROXCUBE

DATA SHEET

EC70 EC cores and accessories

Supersedes data of February 2002


2004 Sep 01



CORE SETS

Effective core parameters

SYMBOL	PARAMETER VALUE		UNIT
Σ(I/A)	core factor (C1)	0.514	mm ⁻¹
V _e	effective volume	40100	mm ³
l _e	effective length	144	mm
A _e	effective area	279	mm ²
A _{min}	minimum area	211	mm ²
m	mass of core half	≈ 127	g



Core halves

A_L measured in combination with an non-gapped core half, unless stated otherwise.

GRAD	E	A _L (nH)	μ _e	AIR GAP (μm)	TYPE NUMBER
3C81	sup	250 ± 3% ⁽¹⁾	≈ 102	≈ 1830	EC70-3C81-E250
		$315 \pm 3\%^{(1)}$	≈ 130	≈ 1370	EC70-3C81-E315
		$400 \pm 3\%^{(1)}$	≈ 165	≈ 1020	EC70-3C81-E400
		$630 \pm 5\%$	≈ 256	≈ 580	EC70-3C81-A630
		$1000 \pm 10\%$	≈ 406	≈ 320	EC70-3C81-A1000
		≥ 4000	≥ 1620	≈ 0	EC70-3C81
3C90	sup	$250 \pm 3\%^{(1)}$	≈ 102	≈ 1830	EC70-3C90-E250
		$315 \pm 3\%^{(1)}$	≈ 130	≈ 1370	EC70-3C90-E315
		$400 \pm 3\%^{(1)}$	≈ 165	≈ 1020	EC70-3C90-E400
		$630 \pm 5\%$	≈ 256	≈ 580	EC70-3C90-A630
		$1000 \pm 10\%$	≈ 406	≈ 320	EC70-3C90-A1000
	Ī	3900 ± 25%	≈ 1580	≈ 0	EC70-3C90

Note

1. Measured in combination with an equal gapped core half (symmetrical air gap).

Properties of core sets under power conditions


	B (mT) at	CORE LOSS (W) at		
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	
3C81	≥330	≤ 8.2	-	
3C90	≥330	≤ 4.9	≤ 5.1	

EC70

COIL FORMERS

General data 8-slots EC70 coil former for insertable pins

PARAMETER	SPECIFICATION
Coil former material	polyamide (PA6.6), glass-reinforced, flame retardant in accordance with "UL 94V-0"; UL file number E44716(M)
Maximum operating temperature	130 °C, "IEC 60085", class B



Winding data 8-slots EC70 coil former for insertable pins; see note 1

NUMBER OF SECTIONS	MINIMUM WINDING AREA (mm²)	NOMINAL WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	TYPE NUMBER
1	465	41.5	97.3	CP-EC70-1S


Note


1. Coil formers with inserted pins are available on request.


MOUNTING PARTS


General data and ordering information


ITEM	REMARKS	MOUNT	FIGURE	TYPE NUMBER
Insertable pins	solderability: "IEC 68-2-20", Part 2,	general	3	PIN-EC
	Test Ta, method 1	horizontal	4	PIN/H-EC
material: copper-zinc alloy (CuZn), tin-lead alloy (SnPb) plated, transition to lead-free (Sn) ongoing.	vertical	5	PIN/V-EC70	
Clamp	copper-zinc alloy (CuZn)		6	CLM/U-EC70
Base plate 4 holes	aluminium		7	BPL4-EC70











EC cores and accessories

EC70

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION	
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.	
Design-in	des	These products are recommended for new designs.	
Preferred		These products are recommended for use in current designs and are available via our sales channels.	
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.	