

Weight: 7.400 (g)

Part Type Information

Multiple single turn or multi-turn printed circuit EMI suppression beads are available in two Fair-Rite materials. The broadband 44 material and in the high frequency 52 material grade.

-PC Beads can be supplied with lower component heights 'C'. Also, the wire length 'F' can be modified to specific requirements.

-Wires are oxygen free high conductivity copper with a lead-free tin coating. Wires on top of the beads are covered with a layer of epoxy.

-PC Beads are controlled for impedance only. The impedances listed are typical values. Minimum impedance values are specified for the + marked frequencies. The minimum guaranteed impedance is the listed impedance less 20%.

-The PC Beads in 44 material are measured on the 4193A Vector Impedance Analyzer. The 52 PC Beads are tested for impedance on the 4191A RF Impedance Analyzer.

-Recommended operating and storage temperature for the PC Beads is -55°C to +125°C.

-Explanation of Part Numbers: Digits 1&2 = product class, 3&4 = material grade and last digit 1 = standard wire length 2.4 mm (.095") minimum.

Fair-Rite Products Corp. Your Signal Solution®

Ferrite Components for the Electronics Industry Fair-Rite Products Corp. PO Box J.One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com Fair-Rite Product's Catalog Part Data Sheet, 2952770302 Printed: 2010-11-09



Mechanical Specifications

mm	mm	nominal	inch
	tol	inch	misc.
13.45	±0.25	0.530	-
11.20	-0.50	0.430	-
11.80	Max	0.464	Max
2.54	±0.10	0.100	-
7.60	±0.20	0.300	-
3.10	Min	0.122	Min
0.65	-	-	22 AWG
-	-	-	-
-	-	-	-
-	-	-	-
	13.45 11.20 11.80 2.54 7.60 3.10	tol 13.45 ±0.25 11.20 -0.50 11.80 Max 2.54 ±0.10 7.60 ±0.20 3.10 Min	tol inch 13.45 ±0.25 0.530 11.20 -0.50 0.430 11.80 Max 0.464 2.54 ±0.10 0.100 7.60 ±0.20 0.300 3.10 Min 0.122

Electrical Specifications

Typical Impedance (Ω)		
100 MHz	320	
250 MHz+	460	
500 MHz+	395	
1000 MHz	300	

Electrical Properties	

Land Patterns

V	W ref	Х	Y	Z
-	-	-	-	-
-	-	-	-	-

Winding Information

Turns	Wire	1st Wire	2nd Wire
Tested	Size	Length	Length
-	-	-	-

Reel Information

Tape Width	Pitch	Parts 7 "	Parts 13 "	Parts 14 "
mm	mm	Reel	Reel	Reel
-	-	-	-	-

Package Size

Pkg Size
-
(-)

Connector Plate

# Holes	# Rows
-	-

Legend

+ Test frequency

Preferred parts, the suggested choice for new designs, have shorter lead times and are more readily available.

The column H(Oe) gives for each bead the calculated dc bias field in oersted for 1 turn and 1 ampere direct current. The actual dc H field in the application is this value of H times the actual NI (ampere-turn) product. For the effect of the dc bias on the impedance of the bead material, see figures 18-23 in the application note How to choose Ferrite Components for EMI Suppression.

A ½ turn is defined as a single pass through a hole.

I/A - Core Constant

A_e: Effective Cross-Sectional Area

 A_{I} - Inductance Factor $\left(\frac{L}{N^{2}}\right)$

N/AWG - Number of Turns/Wire Size for Test Coil

I e: Effective Path Length

Ve: Effective Core Volume

NI - Value of dc Ampere-turns



Fair-Rite Product's Catalog Part Data Sheet, 2952770302 Printed: 2010-11-09



Ferrite Material Constants

Specific Heat	0.25 cal/g/ºC
Thermal Conductivity	10x10 ⁻³ cal/sec/cm/°C
Coefficient of Linear Expansion	8 - 10x10 ⁻⁶ /°C
Tensile Strength	4.9 kgf/mm ²
Compressive Strength	42 kgf/mm ²
Young's Modulus	15x10 ³ kgf/mm ²
Hardness (Knoop)	650
Specific Gravity	\approx 4.7 g/cm ³
The above quoted properties are typical for Fair-Rit	e MnZn and NiZn ferrites.

See next page for further material specifications.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

A new high frequency NiZn ferrite material, that combines a high saturation flux density and a high Curie temperature.

SM beads, PC beads and a range of rod cores are available in this material.


Fair-Rite Product's Catalog Part Data Sheet, 2952770302 Printed: 2010-11-09



52 Material Specifications:


Property	Unit	Symbol	Value
Initial Permeability @ B < 10 gauss		μ	250
Flux Density	gauss	в	4200
@ Field Strength	oersted	н	10
Residual Flux Density	gauss	B,	2900
Coercive Force	oersted	Ho	0.60
Loss Factor	10-6	tan δ/μ _i	45
@ Frequency	MHz		1.0
Temperature Coefficient of Initial Permeability (20 -70°C)	%/°C		1.0
Curie Temperature	°C	Te	>250
Resistivity	Ωcm	ρ	1x10 ⁹


Flux Density vs. Temperature




and H=10 oersted.







using the HP 4284A and the HP 4291A.




Initial Permeability vs. Temperature


Complex Permeability vs. Frequency



Fair-Rite Product's Catalog Part Data Sheet, 2952770302 Printed: 2010-11-09



Impedance, reactance, and resistance vs. frequency.



Impedance vs. frequency with dc bias.