

1. Material Substrate GaAs (N Type)
Epitaxial Layer AlGaAs (P/N Type)

2. Electrode N(Cathode) Side Gold Alloy
P(Anode) Side Gold Alloy


3. Electro-Optical Characteristics

Parameter	Symbol	Min	Typ	Max	Unit	Condition
Forward Voltage	V_F			2.0	V	IF=50mA
Reverse Current	V_R	8			V	IR=10uA
Power	P_O	9			mW	IF=50mA
Wavelength	λ_P		770		nm	IF=50mA
	$\Delta\lambda$		30		nm	IF=50mA

※ Note : Power is measured by Sorter E/T system with bare chip.

4. Mechanical Data

- (a) Emission Area ----- 15.0mil x 15.0mil
- (b) Bottom Area ----- 16.0mil x 16.0mil
- (c) Bonding Pad ----- 130um
- (d) Chip Thickness ----- 7.8mil



AUK Corp.

Eoyang factory, 513-5 Eoyang-dong, Iksan, 570-210, Korea

Tel. +82 63 839 1111 Fax. +82 63 835 8259

www.auk.co.kr

